

TECHNICAL INFORMATION
**FLEXIBLE PACKAGING
 POLYESTER FILM - PMLG**

PROPERTIES		UNITS	TEST METHOD	12 MICRON
NOMINAL THICKNESS		my	PCL METHOD	12
OPTICAL DENSITY			PCL METHOD	1.8
TENSILE STRENGTH AT	MD	Kg/cm2 (kpsi)	ASTM D 882	2100
	TD	Kg/cm2 (kpsi)		2200
ELONGATION AT BREAK	MD	%	ASTM D 882	120
	TD	%		110
HEAT SHRINKAGE (195 Deg. C/15 minutes)	MD	%	ASTM D 1204	4.0
	TD	%		(0.4) Neg

OFFICE: NEW IND. ZONE , SOUTH NATANIA , P.O.B. 8380 , 42504 , ISRAEL
E-mail: rami@jolybar.com TEL. +972-9 -8850848 FAX. +972-9 - 8850849

This document was created with Win2PDF available at <http://www.daneprairie.com>.
The unregistered version of Win2PDF is for evaluation or non-commercial use only.