

**TECHNICAL INFORMATION**

**FLEXIBLE PACKAGING**

**BLISTER BOTTOM LAMINATE , COLD-FORM (Alu-Alu)**

**PRESENTATION**

Aluminium dull side laminated to OPA film , bright side laminated to PVC film.

Winding sense , width (tolerance +/- mm. 0.50) , inside and outside diameter,

Type of core according to customers' specification.

Store in dry and clean area. The laminate should be conditioned for 24 hours at working temperature before use.

Shelf life , when properly stored , maximum 2 years.

MATERIAL	THICKNESS (MY)	WEIGHT g/m <sup>2</sup>	TOLERANCE +/-
ORIENTED POLYAMIDE FILM	25	28.8	10%
ADHESIVE , POLYESTER/POLYURETHANE		4.00	0.50
ALUMINIUM SOFT FOIL PURITY 98% MIN	45	121.50	8%
ADHESIVE , POLYESTER/POLYURETHANE		4.00	0.50
PVC RIGID FILM	60	79.20	10%
OVERALL	138	237.50	10%

This document was created with Win2PDF available at <http://www.daneprairie.com>.  
The unregistered version of Win2PDF is for evaluation or non-commercial use only.