

Polyester in Sheets - GDZG050

Facestock:

A white and clear Polyester.

Laminate Data:

Facestock		Liner		Total ±10%	
Type	Caliper (μ)	Type	gsm	Caliper (μ)	Weight (gsm)
Polyester White	50	cck	135	200	226
Polyester Clear	50	cck	135	200	226

Description:

Filmic facestock permanent acrylic adhesive with high moistures resistance.

Temperature:

Min' application: > 0°C

Service: -20°C/100°C

Performance and Use:

This adhesive has been specially developed for use with clear filmic face materials, providing a strong bond to polar, and non-polar, substrates alike.

It may be used where good transparency is required in combination with clear films.

Initial Tack	10N / 25mm	FTM9 glass
Peel Adhesion 180°C	11N / 25mm	FTM1 St.St

Printing methods:

Suitable for various printing methods, including: Laser printing, Thermal transfer, Letterpress, Offset, Flexo and silk screen printing.

Shelf life:

2 years under storage conditions as defined by FINAT.

Temperature: 20-25°C

Humidity: 40-50% RH

All figures to be considered as typical values.

E-mail: jolybar@jolybar.com

Internet Sites: www.jolybar.com | www.ecojo-nature-packs.com | www.jolycake.com