


SEALPHANE 10.63HT



CORONA Treatment
 PET Homopolymer
 HEAT SEALABLE Copolymer - PEELABLE

TRANSPARENT, biaxially oriented polyester film,
 with CORONA treatment on one side
 and HEAT SEALABLE - PEELABLE on the opposite side.

Characteristics

- SEALPHANE 10.63HT is a transparent polyester film with CORONA treatment on one side and a COEXTRUDED layer of CO-POLYMER adhesive on the opposite side;
- The CORONA treated side can be used for enhanced adhesion for printing and lamination;
- High barrier against gas, water vapor and aroma;
- Large sealing temperature range without deformation: from 130 to 210°C;
- Food can be heated/cooked in contact with SEALPHANE 10.63HT until 210°C - at higher temperatures the film begins to warp;
- Self venting effect when heated in conventional and microwave ovens;
- SEALPHANE 10.63HT can withstand freezing temperatures down to -40°C;
- Dual ovenable with non-stick properties;
- SEALPHANE 10.63HT complies with international regulations for food contact. Specific documents are available upon request.

Sealing Performance	Sealing Temperature		
	130°C	165°C	210°C
To PET Substrates			Easy Peel / No Shredding
To Itself		Easy Peel / No Shredding	
To Contaminated Substrates			Easy Peel / No Shredding
To PET Substrates for Venting		Easy Peel / Venting	
To Itself for Venting	Easy Peel / Venting		
To PP, PE and PS	10.64 suggested		

*PET Substrates: CPET, APET, PETG, rPET and PET coated paper trays, bottles or containers.
 *Contaminated substrates: trays, bottles or containers with sauce or grease contaminating the rim or other sealing surface.

Applications

Suitable for applications where there is a need for easy-open effects, like tray lids or safety seals.

Seals onto, and peels cleanly from, itself or substrates such as APET, CPET, modified CPET, PETG, rPET, PVC, PC, PLA, PET film or PET coated paperboard.

Typical Values

PROPERTIES		Analysis Methods	Unit	Typical Values	
Thickness		ASTM E 252	µm	20	25
Basis weight		ASTM D 646	g/m ²	28	35
Yield		ASTM D 646	m ² /kg	35,7	28,6
Tensile strength at break	MD	ASTM D 882	kgf/mm ²	18	
	TD			16	
Elongation at break	MD	ASTM D 882	%	135	
	TD			95	
Initial modulus	MD	ASTM D 882	kgf/mm ²	370	
	TD			410	
Haze		ASTM D 1003	%	12	14
Shrinkage	MD	150°C / 30 min	%	1,0	
	TD			-0,2	
Coefficient of friction (Side A x Side B)	Static	ASTM D 1894	-	0,6	
	Dynamic			0,6	
Water vapour transmission rate		ASTM F 1249 38°C - 90% RH	g/m ² .day	25	20
Oxygen transmission rate		ASTM F 1927 25°C - 85% RH	cm ³ /m ² .day	70	60
Heat seal strength (Sealable side x Sealable side)		Film/Film @ 110°C; 2,3 bar; 1 sec	gf/pol	700	800
Surface tension (CORONA side)		ASTM D 2578	Dyne/cm	56	

Note:

The information and suggestions contained herein represent the best information available to TERPHANE INC. and we believe them to be reliable. They should not, however, be construed as controlling and are presented without guarantee of performance either express or implied. We urge purchasers to conduct confirmatory tests to determine final suitability for their specific end uses. No statement with respect to use is intended as a positive recommendation for such use and no warranty with respect to infringement of patents held by others is made or intended.

For additional information, please contact our commercial department.

March 2013



Av. Eng. Luiz Carlos Berrini, 1.645 - 9th floor - CEP 04571-011, Brooklin Novo - São Paulo - SP - Brazil
 Tel.: [55 11] 2714-3972 and 2714-3963 - Fax.: [55 11] 2714-3978
 exportsales@terphane.com
www.terphane.com