



Technical datasheet No.: **1882.10**
Product: VALMEX® AIRTEX® magic FR
Article No.: 7535 5946

Type of coating and finish			
Type of coating		PVC	
Burning behaviour		D.M. 26.06.84 (UNI 9177): CL. 1, NFP 92507: M2, ÖNorm: B1, EN 13501-1: B-s2-d0, DIN 4102: B1, ASTM E 84 Class A, NFPA 701 Test 2	
for Burning behaviour		always check validity of fire certificate, also check country-specific validity	
Total weight		350 g/m²	EN ISO 2286-2
Tensile strength	warp/weft	1200 / 1000	N/50 mm EN ISO 1421/V1
Tear strength	warp/weft	130 / 80	N DIN 53363
Cold resistance		-20 °C	EN 1876-1
High Temperature		+70 °C	PA 07.04 (intern)
Light fastness		>6	Note, Value EN ISO 105 B02
Crack resistance	no cracks	100000 x	DIN 53359 A
Base fabric			
Material		PES	DIN EN ISO 2076
Weave		L 1/1	ISO 3572

These indicated technical data are based on average results. Due to production procedures deviations up to -5% can occur. All technical data are in accordance with the present standard of knowledge and give product information without legal binding. All data apply to new products. Applications suggested do not release the customer to test material for its intended application.