



# Ekman

Ekman & Co AB  
Lilla Bommen 1  
PO Box 230  
SE 401 23 Gothenburg, Sweden  
+46 31 750 55 00, FAX +46 31 750 56 80 [info@ekman-co.se](mailto:info@ekman-co.se)

Grammage (g/m <sup>2</sup> )	Opacity (%)	Thickness (µm)	Bulk (thickness/grammage)	Whiteness (CIE)	Brightness (ISO 2470/D65 %)	Smoothness (PPS, µm)	Surface Gloss (TAPPI T 480: 75°, g.u.)
70	87.5	68	0.96	117	95	2.8	<25
80	90.5	77	0.96	117	95	2.8	<25
90	92	87	0.97	117	95	2.8	<25
100	93.5	98	0.98	117	95	2.8	<25
115	96	113	0.98	117	95	2.8	<25
130	97	129	0.99	117	95	2.8	<25
150	98	150	1.0	117	95	2.8	<25
170	98.5	172	1.01	117	95	2.8	<25
200	99	203	1.02	119	97	2.2	<30
250	99.5	255	1.02	119	97	2.2	<30

Screen recommended, max 175 lpi

Values are targets only and can be subject to changes over time without prior notice.