



Technical datasheet No.: **1038.9**

Product: POLYMAR® high gloss

Article No.: 8210 5240

Type of coating and finish			
Type of coating		PVC	
Finish		both sides lacquered, high gloss	
Burning behaviour		ISO 3795 <100 mm/min.	
<hr/>			
Total weight		650 g/m ²	EN ISO 2286-2
<hr/>			
Tensile strength	warp/weft	2500 / 2500 N/50 mm	EN ISO 1421/V1
<hr/>			
Tear strength	warp/weft	250 / 250 N	DIN 53363
<hr/>			
Adhesion		20 N/cm	PA 09.03 (intern)
<hr/>			
Cold resistance.		-40 °C	EN 1876-1
<hr/>			
High Temperature		+70 °C	PA 07.04 (intern)
<hr/>			
Light fastness		>6 Note, Value	EN ISO 105 B02
<hr/>			
Crack resistance	no cracks	100000 x	DIN 53359 A
<hr/>			
Base fabric			
Material		PES	DIN EN ISO 2076
Yarn count		1100 dtex	DIN EN ISO 2060
Weave		L 1/1	ISO 3572

These indicated technical data are based on average results. Due to production procedures deviations up to -5% can occur. All technical data are in accordance with the present standard of knowledge and give product information without legal binding. All data apply to new products. Applications suggested do not release the customer to test material for its intended application.