



Technical datasheet No.: **1040.7**
Product: POLYMAR® Side Curtain
Article No.: 8556 5240

Type of coating and finish			
Type of coating		PVC	
Finish		both sides lacquered, high gloss	
Burning behaviour		ISO 3795 <100 mm/min.	

Total weight		900 g/m ²	EN ISO 2286-2
Tensile strength	warp/weft	4300 / 4000 N/50 mm	EN ISO 1421/V1
Tear strength	warp/weft	500 / 500 N	DIN 53363
Adhesion		20 N/cm	PA 09.03 (intern)
Cold resistance.		-40 °C	EN 1876-1
High Temperature		+70 °C	PA 07.04 (intern)
Light fastness		>6 Note, Value	EN ISO 105 B02
Crack resistance	no cracks	100000 x	DIN 53359 A / DIN EN ISO 7854 B

Base fabric			
Material		PES	DIN EN ISO 2076
Yarn count		1100 dtex	DIN EN ISO 2060
Weave		P 2/2	ISO 3572

Remarks	complies with EN 12641-2, materials		
---------	--	--	--

These indicated technical data are based on average results. Due to production procedures deviations up to -5% can occur. All technical data are in accordance with the present standard of knowledge and give product information without legal binding. All data apply to new products. Applications suggested do not release the customer to test material for its intended application.